




Tradition Exotic

HDF 9 MM | 1261 x 131.5 MM | 49.6457 x 5.177 INCH | 4.1371 x 0.41371 FT | 10 PLANKS/PACK | 1.6582 M³/PACK = 17.8487 FT³/PACK | 14 KG/PACK = 30.86 POUND/PACK | 50 PACKS/PALLET | 790 KG/PALLET = 1742 POUND/PALLET




PEFC certified
This product is from sustainably
managed forest and controlled
sources. www.pefc.org



2 SOFT SHEEN
FINISH

3 GENUINE WOOD
STRUCTURE

> **NARROW PLANKS** <
+ 4-SIDED MICRO V-GROOVE 131 mm



AC 4



EN 13329 : 2006



EN14041:2004 1161

Tradition Exotic

Edition 2009 Versie 2009 Edition 2009 Edition 2009	Method Methode Méthode Methode	Parameters Parameters Paramètres Parameter	Norm requirements Normvereisten Exigences de norme Normvorschriften	Values Waarden Valeurs Werte
Class of use Gebruiksklasse Classe d'utilisation Nutzungsklasse	EN 13329		Class 32 Klasse 32 Classe 32 Klasse 32	All residential use up to commercial use Van residentieel ot commercieel gebruik Toutes, de l'utilisation résidentielle à l'utilisation commerciale Alle, von der Wohn- bis zur Gewerbenutzung
Wear resistance Slijtageweerstand Classe de résistance Verschleißwiderstand	EN 13329		≥ 4000	≥ 4000
Wearclass Slijtageklasse Classe de résistance Widerstandsklasse	EN 13329		AC 4	AC 4
Thickness swelling Dikte zwellung Gonflement d'épaisseur Quelldicke	EN 13329		≤ 18 %	± 6 %
General aspect of installed flooring Algemeen aspect van geïnstalleerde vloer Aspect général du plancher installé Allgemeiner Zustand des Untergrundfußbodens	EN 13329	Height Difference Hoogteverschil Différence de hauteur Höhenunterscheid	≤ 0,15 mm	0,10 mm
		Openings Openingen Ouvertures Öffnungen	≤ 0,20 mm	0,10 mm
		Flatness length Lengte vlakheid Longeur aspect plat Ebenheit Länge	Concave Concaaf Concave Konkav ≤ 0,50 % Convex Convex Convexe Konvex ≤ 1,00 %	≤ 0,50 % ≤ 1,00 %
		Flatness width Breedte vlakheid Largeur aspect plat Ebenheit Breite	Concave Concaaf Concave Konkav ≤ 0,15 % Convex Convex Convexe Konvex ≤ 0,20 %	≤ 0,15 % ≤ 0,20 %
Impact class Impactklasse Classe d'impact Aufprallklasse	EN 13329		IC2	IC2
Staining Spatten Taches Fleckenbildung	EN 438-2,15 UE Atc D.3		5 (Group 1&2) 4 (Group 3)	5 (Group 1&2) 4 (Group 3)
Light Fastness Lichtvastheid Résistance à la lumière Lichtbeständigkeit	EN 438-2,16		≥ 6	7
Burning cigaret Brandende sigaret Brûlures de cigarettes Zigarettenbrand	EN 438-2,18 UE Atc D.4		4	4
Movement of furniture feet Beweging van meubelpoten/-wielotjes Mouvement des pieds de meubles Bewegung von Möbelfüßen	EN 424			No damage Geen schade Pas de dommages Keine Beschädigungen
Castor Chairs Stoelen op wielotjes Chaises à roulettes Rollstühle	EN 425			No damage Geen schade Pas de dommages Keine Beschädigungen
Slip resistance Slip weerstand Résistance aux glissements Rutschfestigkeit	EN 13893 2002		Class DS: ≥ 0,30 µ	Class DS
Emission of formaldehyde Formaldehyde-emissie Emission de formaldyhyde Formaldehydausdünstung	EN 717-2		Class E1: ≤ 3,5 mg/m².h	Class E1
Reaction to fire Brandreactie Reaction au feu Feuerfestigkeit	EN 13501-1 (2002)		Efl S1	Cfl S1
Thermal resistance Thermische weerstand Résistance thermique Wärmewiderstand	ISO 8302 1991		max. 0,15 m² K/W	R = 0,057 (m².K/W)
Underfloor heating Ondervloerverwarming Chauffage par sol Fußbodenheizung		Specific instructions Specifieke instructies Instructions spécifiques Besondere Nutzungsanweisungen		OK